

PLA	Nominal Value *	Unit	Test Method
Physical			
Specific Gravity	1.24	g/cc	ASTM D 792

Hardness			
Shore D Hardness	84		ASTM D 2240

Mechanical			
Tensile Modulus (73.4° F)	480000/560000	psi	D882 (MD/TD)
Tensile Strength - (Yield, 73.4° F)	16000/21000	psi	D882 (MD/TD)
Tensile Strength - (Break, 73.4° F)	N/A	N/A	N/A
Elongation - (Yield, 73.4° F)	N/A	N/A	N/A
Elongation - (Break, 73.4° F)	160/100	%	D882 (MD/TD)
Flexural Modulus (73.4° F)	N/A	N/A	N/A

Impact			
Notched Izod Impact (73.4° F)	0.3 - 0.35	ft-lb/in	ASTM D 256

Thermal			
Heat Deflection Temperature Under Load (66 psi, Unannealed)	N/A	N/A	N/A
(264 psi, Unannealed)	N/A	N/A	N/A
Vicat Softening Temp	N/A	N/A	N/A

Electrical			
Volume Resistivity	N/A	N/A	N/A
Surface Resistivity	N/A	N/A	N/A

Flammability			
Flame Rating	V2		UL 94

Recommended Settings			
Nozzle Temperature	190 - 215	°C	
Heated Bed Temperature	Ambient - 45	°C	
Nozzle	1.75	mm	
Print Speed	up to 200	mm/s	
Layer Height:	0.1-0.4	mm	
Infill	As needed up to 100%		
Perimeter	minimum 0.9	mm	
Minimal Layer Time:	4	seconds	

***ASTM & ISO Properties**

Note - Typical properties: these are not to be construed as specifications

ABS	Nominal Value	Unit	Test Method
Physical			
Specific Gravity	1.04		ASTM D 792

Hardness			
Rockwell R Hardness	112	g/cc	ASTM D 785

Mechanical			
Tensile Modulus (73.4° F)	328559	psi	ASTM D 638
Tensile Strength - (Yield, 73.4° F)	6258	psi	ASTM D 638
Tensile Strength - (Break, 73.4° F)	4694	psi	ASTM D 638
Elongation - (Yield, 73.4° F)	2	%	ASTM D 638
Elongation - (Break, 73.4° F)	24	%	ASTM D 638
Flexural Modulus (73.4° F)	332826	psi	ASTM D 790

Impact			
Notched Izod Impact (73.4° F)	5.879	ft-lb/in	ASTM D 256

Thermal			
Heat Deflection Temperature Under Load	N/A	N/A	N/A
(66 psi, Unannealed)	201.2	°F	ASTM D 648
(264 psi, Unannealed)	176	°F	ASTM D 648
Vicat Softening Temp	208	°F	ISO 306

Electrical			
Volume Resistivity	N/A	N/A	N/A
Surface Resistivity	N/A	N/A	N/A

Flammability			
Flame Rating	HB		UL 94

Recommended Settings			
Nozzle Temperature	210 - 245	°C	
Heated Bed Temperature	110 - 120	°C	
Nozzle	1.75	mm	
Print Speed	up to 200	mm/s	
Layer Height:	0.1-0.4	mm	
Infill	As needed up to 100%		
Perimeter	minimum 0.9	mm	
Minimal Layer Time:	2	seconds	

Color	Pantone	PLA	ABS	Available
Black	Black C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Green	360 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Blue	285 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Red	186 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
White	N/A	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Yellow	Yellow C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Purple	268 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Orange	1585 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Gray	Cool Gray 6 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Neon Green	804 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes
Neon Orange	802 C	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes

No Pigment				
Natural	N/A	1.75 mm / 2.85 mm	1.75 mm / 2.85 mm	Yes

Diameter & Accuracy		Nominal 1.75 mm \pm 0.03 mm Nominal 2.85 mm \pm 0.03 mm		
Ovality Accuracy		\pm 0.03mm		

Retail Packaging		Vacuum sealed resealable zip top bag with desiccant in a cardboard box		
Labeling		Tamper Evident Label with UPC GTIN-12, Manufacture date, Recommended optimal print temperature and spool specifications		
Small Box - 220g / Student Spool		152mm x 152mm x 50.8mm		
Medium Box - 1 kg / 650 g Spool		214.4mm x 214.4mm x 75.4mm		
Master Box Quantity	Pack Quantity			
Small Box - 220g / Student Spool	13			
Medium Box - 1 kg / 650 g Spool	6			

Spool	Small	Medium	Large
Spool Diameter	152.4 mm	212 mm	203.2 mm
Spool Width \ Thickness	35.44 mm	40 mm	73.15 mm
Hub Hole Diameter	53.9 mm	52.71 mm	52.71 mm
Material Net Weight	220 g \pm 5 g	650 g \pm 5 g	1 kg \pm 5 g
Gross Weight	430.58g	894g	1728g



We make filament so you can make [Anything!](#)

